

# Titanium Alloy TA6V Ti-6Al-4V

# SPECIFICATIONS

UNS: R56400

# **TYPICAL MECHANICAL PROPERTIES**

#### • Annealed condition:

- Tensile test at ambient temperature:
  - UTS: >896 N/mm<sup>2</sup>
  - 0.2 % Yield strength: > 827 N/mm<sup>2</sup>

10 %

- Elongation (5d):

# COMPOSITION

Aluminum	6.00
Vanadium	4.00
Carbon	<0.08
Iron	<0.30
Oxygen	<0.20
Nitrogen	<0.07
Titanium	Base

## APPLICATIONS \_\_\_\_

- Aerospace and energy industry: discs, compressor blades, structural parts, fasteners for low and high temperature environments, etc.
- Chemical industries

### CHARACTERISTICS

- This titanium alloy has good resistance to fatigue, crack propagation, corrosion and creep (up to 300°C).
- Alpha-beta titanium alloy.

### HEAT TREATMENT

- Anneal (Normally this alloy is used in the annealed condition):
  - Heat to 700/750 °C
  - Hold 2 or 4 hours depending on section
  - Air cool

- Heat treated (for section < 40 mm):
  - Solution treatment
  - Heat to 825/950 °C water cool
  - Ageing
  - In the range 450-590°C, depending on properties required

### PHYSICAL PROPERTIES

• Density:	4.43	• Electrical resistivity in $\mu\Omega.cm^2$		
		- at 20°C: 170		
<ul> <li>Mean coefficient of expansion in m/m.°C:</li> <li>between 20°C and 200°C: 9.0 x 10<sup>-6</sup></li> </ul>		<ul> <li>Absolute magnetic permability in H/m: 1.26 x 10<sup>-6</sup></li> </ul>		
		Critical points:		
<ul> <li>Modulus of elasticity in N/mm<sup>2</sup>:</li> </ul>		- Beta Transus: 1000°C		
- at 20°C:	110 x 10 <sup>-3</sup>			
• Torsional modulus in N/mm <sup>2</sup> : 45000				
• Thermal conductivity in W.m/m <sup>2</sup> .°C:				
- at 20°C:	6.7			

# Forging \_\_\_\_\_

<ul> <li>Breakdown temperature:</li> </ul>	1050°C - 1100°C
<ul> <li>Finishing temperature:</li> </ul>	850°C - 950°C

#### Contact:

#### www.aubertduval.com

The data provided in this document represent typical or average values rather than maximum or minimum guaranteed values. The applications indicated for the grades described are given as guidance only in order to help the reader in his personal assessment. Please note that these do not constitute a guarantee whether implicit or explicit as to whether the grade selected is suited to specific requirements. Aubert & Duval's liability shall not under any circumstances extend to product selection or to the consequences of that selection.